



CLASSIC



Tehnički list

Gustina	1200 kg/m ³	ISO 1183-1/Metod A	
Prag savitljivosti	2 - 4	ISO 6603-2	
Modul elastičnosti	4000 -4.500 N/mm ²	TS EN 310	
Pritisna snaga	34,2 N/mm ²	TS EN 310	
Apsorpcija vode	Težina %	0,7	EN 317
	Debljina %	0,1	
Linearno proširenje	0,15%	EN 479	
Omekšavanje po Vicat-u	85 - 95 C°	ISO 306/Metod B	